

2.5/0.55 Dryback Technical Specification		
	Standard	Standard(Result)
Thickness	EN428	(-0.10,+0.13)
Size & Pack Quantity	Plank	184 x 1219mm 18 planks/4.04m ²
Wear Layer	EN428	0.55mm
Surface treatment	ASTM D523	Ceramic Bead Coating
Bevelled edge	Standard Bevel	Four Sided Micro Bevel
Pack Weight		18kg
Classification	ISO 10874 Commercial	33
	ISO 10874 Domestic	23
Squareness	EN427	≦ 0.25mm
Edge Straightness	EN427	≦ 0.25mm
Openings between	ISO 10582 Annex C	O max ≦ 0.20mm O ave ≦ 0.15mm
Height Difference(Assembled)	ISO 10582 Annex C	H max ≦ 0.15mm H ave ≦ 0.10mm
Gloss Unit	ASTM D523	5±1°
Reaction to fire	EN1350-1/ISO 9239-1-2003	Bf1-s1/CHF 9Kw/m ² SM 74%
Light fastness	EN ISO 105-B02	pass ≧ 6
Scratch resistance	ISO 1518	≧2500 g
Dimensional stability (80°C/6h)	EN 434	≦0.15%
Curling After Exposure to Heat (80°C/6h)	EN434	-1.50mm≦n≦1.20mm
Peel Resistance	EN431	≧50 N / 5cm
Slip resistance	DIN 51130:2014/AS 4586:2013	R10/P3
Resistance to Staining	ASTM F925-13	No change
Formaldehyde Emission	EN 717-1	Not detected
Phthalate Content	EN14372:2014	Not detected
Underfloor Heating Suitability		Yes, ≦27°C
Recycling		Suitable
Installation Method		Glue down
Castor Chair	ISO 4918	25000 cycles
Certification Offered		Floorscore, Greenguard, CE
Warranty	Commercial Surface Guarantee	15 Years
	Residential Surface Guarantee	Lifetime