























Technical specifications

Marmoleum meets the requirements of EN-ISO 24011.

Marmoleum Acoustic meets the requirements of EN 687.

Marmoleum Decibel meets the requirements of EN 686.

		Marmoleum Real/Fresco	Marmoleum Real/Fresco/ Vivace	Marmoleum Real/Fresco	Marmoleum Real	Marmoleum Decibel	Marmoleum Acoustic
 Total thickness	EN-ISO 24346	2.0 mm	2.5 mm	3.2 mm	4.0 mm	3.5 mm	4.0 mm
 Domestic: heavy	EN-ISO 10874	Class 23	Class 23	Class 23	Class 23	Class 23	Class 23
 Commercial: general/heavy/ very heavy	EN-ISO 10874	Class 32	Class 34	Class 34	Class 34	Class 33	Class 33
 Light Industrial: moderate/ general/heavy	EN-ISO 10874	Class 41	Class 43	Class 43	Class 43	Class 41	Class 41
 Roll width	EN-ISO 24341	2.00 m	2.00 m	2.00 m	2.00 m	2.00 m	2.00 m
 Roll length	EN-ISO 24341	≤ 32 m	≤ 32 m	≤ 32 m	≤ 32 m	≤ 32 m	≤ 32 m
 Indentation residual	EN-ISO 24343-1	≤ 0.15 mm	≤ 0.15 mm	≤ 0.15 mm	≤ 0.20 mm	≤ 0.30 mm	≤ 0.40 mm
 Castor chair continuous use	EN 425	Suitable for office chairs with castors.					
 Light fastness	EN-ISO 105-B02	Method 3: blue scale minimum 6.					
 Flexibility	EN-ISO 24344	ø 30 mm	ø 40 mm	ø 50 mm	ø 60 mm	ø 40 mm	ø 60 mm
 Resistance to chemicals	EN-ISO 26987	Resistant to diluted acids, oils, fats and to conventional solvents. Not resistant to prolonged exposure to alkalis.					
 Bacteriostatic properties		Marmoleum has natural bacteriostatic properties, which are confirmed by independent laboratories, even against the bacteria MRSA.					
 Cigarette resistance	EN 1399	Marks left on linoleum as a result of stubbed-out cigarettes can be removed.					
 Slip resistance	AS/NZS 4586	R10	R10	R10	R10	R10	R10
 Acoustical impact sound reduction	EN ISO 717-2	≤ 4 dB	≤ 5 dB	≤ 6 dB	≤ 7 dB	17 dB	14 dB
 Electrical resistance Marmoleum Ohmex	EN 1081	-	1-10 ⁶ < R1 < 1-10 ⁸ Ω static dissipative	-	-	-	-
 Life Cycle Assessment		LCA is the foundation for securing the lowest environmental impact.					
Marmoleum meets the requirements of EN 14041							 EN 14041
 Reaction to fire	C1.10 of the BCA CfI -s1, ISO9239-1						
 Slip resistance	EN 13893	DS: ≥ 0.30					
 Body voltage	EN 1815	< 2 kV					
 Thermal conductivity	EN 12524	0.17 W/m·K					

We will take back this sample book after use please call your local office for collection.



142879 / 01012013



creating better environments

Australia
Forbo Floorcoverings Pty Ltd.
23 Ormsby Place
Wetherill Park
NSW 2164
T +61 2 9828 0200
F +61 2 9725 3456
info.au@forbo.com
www.forbo-flooring.com.au

New Zealand
Forbo Flooring Systems
PO BOX 230 265
Botany 2163 Auckland
T +64 0800 000 563
F +64 0800 000 634
info.nz@forbo.com
www.forbo-flooring.co.nz

Forbo

FLOORING SYSTEMS